

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 343 053 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:

10.09.2003 Bulletin 2003/37

(51) Int Cl.7: **G03G 9/09**, G03G 9/097,
G03G 9/08, G03G 9/083

(21) Application number: **03004507.4**

(22) Date of filing: **28.02.2003**

(84) Designated Contracting States:

**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
HU IE IT LI LU MC NL PT SE SI SK TR**

Designated Extension States:

AL LT LV MK RO

(30) Priority: **01.03.2002 JP 2002056315**

19.07.2002 JP 2002210813

(71) Applicant: **Ricoh Company, Ltd.**

Tokyo 143-8555 (JP)

(72) Inventors:

- **Tosaka, Hachiroh**
Tokyo 143-8555 (JP)
- **Ito, Tomiaki**
Tokyo 143-8555 (JP)
- **Natori, Yuji**
Tokyo 143-8555 (JP)

(74) Representative: **Barz, Peter, Dr.**

**Patentanwalt
Kaiserplatz 2
80803 München (DE)**

(54) **Black toner, production process, image forming method and image forming apparatus using the toner**

(57) A toner for developing an electrostatic latent image, including toner particles each containing a black colorant and a binder resin, wherein the black colorant comprises a metal oxide having a number average par-

ticle diameter in the range of 20 to 100 nm in an amount of 10 to 40 % by weight based on a total weight of the toner particles.

EP 1 343 053 A1

Description

[0001] This invention relates to a toner for developing an electrostatic latent image in electrophotography, electrostatic recording, electrostatic printing and so on, and to a method for producing the toner. More particularly, the present invention is directed to a black toner without using carbon black.

[0002] Carbon black has been conventionally used as a black colorant for a toner for developing an electrostatic latent image in image forming machines such as copying machines, laser printers and facsimile machines. However, because of a problem of carcinogenesis, the use of toners without carbon black has been long desired. While a magnetic material is a black colorant, the use thereof is limited to a magnetic toner. An organic black colorant such as aniline black and a Nigrosine dye has a problem because a high density image is not obtainable.

[0003] Japanese Patent No. 2736680 proposes a black metal oxide pigment composed of Fe_2TiO_5 and Fe_2O_3 - FeTiO_3 and a particle diameter of 0.1 to 0.5 μm . While this black pigment is safe, non-magnetic and heat resistant, it is necessary to use a large amount, i.e. 40 to 60 % by weight based on the weight of the toner, in order to obtain color density comparable to the known carbon black toner. Because of high specific gravity of the black pigment, however, the toner containing such a large amount of the black pigment has 1.4 to 1.8 times as great a specific gravity as that of the conventional carbon black toner. Thus, the black metal oxide pigment poses a lot of problems such as occurrence of abnormality in a toner density sensor or a toner amount sensor and short lifetime of carriers.

[0004] Japanese Patent No. 2997206 proposes a toner containing a black metal oxide pigment composed of oxides of cobalt, manganese and iron and having a specific surface area of 50 to 100 m^2/g . Because of the extremely fine particle size, this black pigment can afford image density comparable to the conventional carbon black colorant even when used in an amount of 10 to 30 % based on the weight of the toner. However, the pigment is apt to form an aggregate and is not uniformly dispersed in the toner. As a consequence, the charging amount of the toner is insufficient and the developing efficiency is not good.

[0005] The present invention has been made in view of the above problems. In accordance with one aspect of the present invention a toner for developing an electrostatic latent image, comprising toner particles each including a black colorant and a binder resin, wherein said black colorant comprises a metal oxide having a number average particle diameter in the range of 20 to 100 nm in an amount of 10 to 40 % by weight based on a total weight of said toner particles.

[0006] In another aspect, the present invention provides a toner container comprising the above toner.

[0007] The present invention also provides an image forming apparatus comprising the above toner container.

[0008] The present invention further provides an image forming method comprising developing an electrostatic latent image with the above toner.

[0009] The present invention further provides a method of preparing a toner, comprising mixing toner particles, each including black metal oxide colorant having a number average particle diameter d of 0.02×10^{-6} to 0.100×10^{-6} [m] and a binder resin, with fine metal oxide powder using a Henschel mixer for a period of time of T [second].

said mixer comprising an inside wall defining a mixing chamber, and a rotating blade having a tip portion and disposed in said mixing chamber such that a clearance C [m] is defined between said tip portion and said inside wall, said mixer being operated such that said tip portion of said rotating blade moves at a peripheral speed of V [m/sec], wherein said number average particle diameter d , clearance C , peripheral speed V and mixing time T satisfy the following condition:

$$(C \times d) / (V \times T) \leq 5 \times 10^{-13}$$

[0010] The present invention will be described in detail below with reference to the accompanying drawing in which:
[0011] FIG. 1 is a sectional view diagrammatically illustrating a Henschel mixer used for mixing an external additive with toner particles.

[0012] A toner according to the present invention comprises toner particles each including a black metal oxide colorant and a binder resin.

[0013] The metal oxide colorant is preferably contains at least one oxide of a metal selected from Al, Si, Ti, V, Mn, Fe, Co, Cu, Nb, Mo and Sn. Examples of the metal oxide colorant include Mn-containing iron oxide pigments having a magnetite or hematite structure, Fe_2O_3 - Mn_2O_3 , sintered TiO_2 , MnFe ferrite, polycrystalline particles composed of a mixed composition of Fe_2TiO_5 and Fe_2O_3 - FeTiO_3 solid solution, surface coated products of the above polycrystalline particles having a coating of an oxide of at least one element selected from Al, Ti, Si, Zr and P, and composite metal oxide pigment having a spinel structure and containing Co, Fe, Cr and, optionally Mn.

[0014] It is important that the black metal oxide colorant have a number average particle diameter in the range of 20 to 100 nm. Too large a number average particle diameter of the black colorant in excess of 100 nm causes a reduction of an image density. When the number average particle diameter is below 20 nm, on the other hand, the colorant fails to uniformly disperse in the binder resin so that the charging amount of the toner is reduced to cause background stains

(fogging) and an increase of the consumption of the toner. The number average particle diameter as used herein is measured using a transmission electron microscope (TEM).

[0015] It is also important that the black metal oxide colorant be present in an amount of 10 to 40 % by weight based on a total weight of the toner particles. Too small an amount of the black metal oxide colorant below 10 % by weight fails to give a satisfactory image density. When the amount is above 40 % by weight, the specific gravity of the toner becomes so high that, when the toner is used together with a carrier as a two-component developer, the service life of the carrier is reduced. For reasons of improved service life of the two-component developer, the amount of the black metal oxide colorant is preferably 10 to 30 % by weight based on a total weight of the toner particles.

[0016] Preferably, the toner according to the present invention has a dielectric loss ($\tan\delta$) in the range of 3×10^{-3} to 15×10^{-3} for reasons of high image density while preventing background stains (fogging), increase of toner consumption and toner scattering.

[0017] As used herein, the dielectric loss ($\tan\delta$) is measured as follows:

Sample toner is pelletized at a pressure of 480 kg/cm² with a pelletizing device (MAEKAWA Testing Machine Type M). The pellet is on a solid electrode (SE-70 manufactured by Ando Denki Co., Ltd.) and measured for the capacitance (Ca) and conductance (Cd) using a dielectric loss meter (TR-10C manufactured by Ando Denki Co., Ltd.) at a frequency (f) of about 1 KHz. The dielectric loss is determined from the following equation:

$$\tan\delta = Ca / (2\pi \times f \times Cd),$$

[0018] The dielectric loss of the toner may be adjusted by controlling the amount of the black metal oxide colorant and/or an additive such as a charge controlling agent in the toner and conditions under which ingredients of the toner are mixed during preparation.

[0019] It is also preferred that the toner have saturation magnetization of not greater than 10 Am²/Kg for reasons of high image density in the case where the toner is used as a two-component developer. The saturation magnetization as used herein is measured using a multi-sample rotary-type magnetization measuring device (Model REM-1 Type 1 manufactured by Toei Industry Co., Ltd.) in a magnetic field of 796 Am²/Kg.

[0020] As the binder resin for use in the present invention, any resin known to be used conventionally for the preparation of a toner can be employed. Illustrative of suitable binder resins are styrene resins (homopolymers or copolymers containing styrene or its homologues) such as polystyrene, poly- α -methylstyrene, styrene-chlorostyrene copolymer, styrene-propylene copolymer, styrene-butadiene copolymer, styrene-vinyl chloride copolymer, styrene-vinyl acetate copolymer, styrene-maleic acid copolymer, styrene-acrylic acid ester copolymer, styrene-methacrylic acid ester copolymer, styrene- α -methyl chloroacrylate copolymer, styrene-acrylonitrile-acrylic acid ester terpolymer; saturated polyester resins, unsaturated polyester resins, epoxy resins, vinyl chloride resins, rosin-modified maleic acid resins, phenol resins, polyethylene resins, polypropylene resins, petroleum resins, polyurethane resins, ketone resins, ethylene-ethylacrylate copolymer, xylene resins, kumaronic acid resins, chlorinated paraffins, and polyvinyl butyrate resins. The resins may be used alone or in combination. Among these binder resins, polystyrene resins or epoxy resins are preferred.

[0021] For the purpose of improving releasing property, the toner may contain a wax. Any wax may be suitably used for the purpose of the present invention. Examples of such waxes include low molecular weight polyolefin waxes such as low molecular weight polyethylene wax and low molecular weight polypropylene wax; synthetic hydrocarbon waxes such as Fischer-Tropsch wax; natural waxes such as carnauba wax, candelilla wax, rice wax, montan wax, Jojoba wax, bees wax, lanolin and spermaceti; mineral waxes such as montan wax and ozokerite; higher fatty acid waxes such as hydrogenated castor oil, hydroxystearic acid, palmitic acid and myristic acid; and metal salts, phenol esters or amides of higher fatty acids. These waxes may be used singly or in combination of two or more thereof. The amount of the wax is generally 0 to 20 % by weight, preferably 1-10 % by weight, based on the weight of the toner.

[0022] The toner of the present invention may contain a charge controlling agent, if desired. Any charge controlling agent generally used in the field of toners for use in electrograph may be used. Examples of charge controlling agents include positive charge imparting agents such as Nigrosine dye, a quaternary ammonium salt including a fluorine-modified quaternary ammonium salt, a basic dye and amino group-containing polymer; and negative charge imparting agents such as chromium-containing monoazo dye, chromium-containing organic dye and metal salts of salicylic acid compounds. The amount of the charge controlling agent is generally 0.1 to 20 % by weight, preferably 0.1 to 10 % by weight, based on the weight of the toner, for reasons of obtaining proper charging characteristics.

[0023] The toner of the present invention may be mixed with an external additive for the purposes of improving the fluidity and so on. Inorganic fine particles may be suitably used as the external additive. Examples of inorganic fine particles include silica, alumina, titanium oxide, barium titanate, magnesium titanate, calcium titanate, strontium titanate, zinc oxide, tin oxide, quartz sand, clay, mica, wallstonite, diatomaceous earth, chromium oxide, cerium oxide, iron

oxide red, antimony trioxide, magnesium oxide, zirconium oxide, barium sulfate, barium carbonate, calcium carbonate, copper oxide, barium oxide, calcium oxide, potassium oxide, sodium oxide, magnesium carbonate, magnesium sulfate, CaO , SiO_2 , K_2O , $(\text{TiO}_2)_n$, $\text{Al}_2\text{O}_3 \cdot 2\text{SiO}_2$, silicon carbide and silicon nitride. Above all, silica, titania or alumina is preferably used. These inorganic fine particles preferably have a primary particle diameter of 5 m μ (5 nm) to 2 μm , more preferably 5 m μ to 500 m μ . By subjecting these external additives, in particular fine metal oxide powder, to a surface treatment to improve the hydrophobic properties thereof, deterioration of the fluidity and the charge properties of the toner can be avoided even under high humidity conditions. Suitable surface treating agents include silane coupling agents, silylating agents, silane coupling agents having a fluorinated alkyl group, silicon oil, organic titanate type coupling agents, and aluminum type coupling agents. Hydrophobic silica is the most preferred external additive for the purpose of the present invention.

[0024] The inorganic fine particles are used in an amount of generally 0.2 to 5 % by weight, preferably 0.3 to 3 % by weight, based on the weight of the toner.

[0025] The external additive may also be fine particles of a polymeric substance such as polystyrene, polyolefins, polytetrafluoroethylene, polymethacrylate or an acrylate copolymer obtained by soap-free emulsion polymerization, suspension polymerization or dispersion polymerization; silicone, benzoguanamine or nylon obtained by polycondensation, zinc stearate, or a thermosetting resin.

[0026] When the above hydrophobic fine metal oxide powder is used as the external additive, it is preferred that the fine metal oxide powder be attached to the toner particles to provide a detaching rate of 30 % by weight or less. The term "detaching rate" as used herein is intended to refer to an amount of the fine metal oxide powder detached from the toner particles, when the toner is sonicated in an aqueous medium containing 1 % by weight of a surfactant at a frequency of 38 kHz and a power of 120 W for 10 minutes.

[0027] More particularly, the detaching rate is measured as follows. Sample toner (4 g) is dispersed in 400 ml of an aqueous solution containing 0.1 % of a surfactant (DRYWELL manufactured by Fuji Film Inc.). The mixture is then subjected to ultrasonic vibration at a frequency of 38 kHz and a power of 120 W for 10 minutes for 10 minutes using an ultrasonic washing device (manufactured by NND Inc.). The sonicated mixture is then allowed to quiescently stand for 24 hours to permit the toner particles to settle. The supernatant is removed and the wet solids are dried in air at 23°C and a relative humidity of 65 % for at least 24 hours. The dried toner particles (3 g) are pelletized at a pressure of 480 kg/cm² with a pelletizing device (MAEKAWA Testing Machine Type M). The pellet is measured for the content of the external additive using fluorescent X-ray analyzer (manufactured by Shimadzu Corporation; X-ray power: 40 kV, 10 mA). In the case of hydrophobic silica, for example, the amount of Si is measured from the fluorescent X-ray intensity using a previously prepared calibration curve. The detaching rate RD is calculated as follows:

$$\text{RD} = (\text{W}_0 - \text{W}_1) / \text{W}_0 \times 100 (\%)$$

where W_0 and W_1 are the weights of the external additive before and after the sonication, respectively.

[0028] When the detaching rate is 30 % by weight or less, the toner gives high quality images not only in the initial stage but also after repeated use for long runs. The detaching rate may be adjusted by controlling mixing force (control of shear rate of a mixer for mixing the external additive and the toner particles) and mixing time (control of the operation time and number of the mixer).

[0029] When the above hydrophobic fine metal oxide powder is used as the external additive, it is also preferred that the fine metal oxide powder be attached to the toner particles using a Henschel mixer as shown in FIG. 1. The mixer comprises an inside wall 1 defining a mixing chamber 2, and a rotating blade 3 having a tip portion 3a and disposed in the mixing chamber 2 such that a clearance C [m] is defined between the tip portion 3a and the inside wall 1. The mixer is operated for a period of time of T [second] such that the tip portion 3a of the rotating blade 3 moves at a peripheral speed of V [m/sec]. In this case, it is preferred that the clearance C, peripheral speed V and mixing time T satisfy the following condition:

$$(\text{C} \times d) / (\text{V} \times \text{T}) \leq 5 \times 10^{-13} [\text{m}]$$

where d is the number average particle diameter [m].

[0030] The clearance C is preferably 0.001 to 0.02 m. The peripheral speed V is preferably 5 to 100 m/sec. The mixing time T is preferably 10 to 1500 seconds. The mixing time T is a total of the actual mixing time when the mixing is operated intermittently. The number average particle diameter d is 0.02×10^{-6} to 0.1×10^{-6} (20 to 100 nm).

[0031] The toner according to the present invention preferably has a bulk density of 0.200 g/cm³ to 0.500 g/cm³, more preferably 0.350 g/cm³ to 0.450 g/cm³, for reasons of reduction of toner scattering and background stains.

[0032] The toner according to the present invention may be used by itself as a one-component toner or may be used

together with a carrier as a two-component developer. As a carrier, there may be used iron powder, glass beads, ferrite powder, nickel powder or a product obtained by applying a resin coating on any of these powder and beads.

[0033] The following examples will further illustrate the present invention. Parts are by weight. In the examples, the image density, color-reproducibility and particle diameter of toner are measured as follows:

Image density:

[0034] An image is fixed on a recording paper such that the amount of the toner of the image is 1.0 mg/cm². The image density at the toner mass of 1.0 mg/cm² is measured with an X-Rite 938 spectrodensitometer using DEN color system at "A" response.

Color reproducibility:

[0035] Color reproducibility in terms of a* and b* values is measured with an X-Rite 938 spectrodensitometer, using D50 illuminant and CIE 2-degree observer at a color density of 0.8.

Particle diameter:

[0036] The volume average particle diameter herein is measured using Multisizer E (manufactured by Coulter Electronics Inc.) with a 100 μ m aperture tube.

Example 1

[0037]

Polyester resin	71 parts
Polyethylene wax	5 parts
MnFe Ferrite (number average particle diameter: 72 nm, saturation magnetization: 0.2 Am ² /Kg)	23 parts
Negative charge controlling agent	1 part

[0038] The above composition was mixed using a Henschel mixer under various conditions to obtain premixed materials having different degrees of mixing state and each having a weight particle diameter of 7.0 μ m. Each of the premixed materials was melted, kneaded with a dual axis kneader, solidified, ground and classified. From the thus obtained various kinds of toner particles having different degree of mixing state, one kind of toner particles having a dielectric loss δ of 12×10^{-3} and a true specific gravity of 1.44 g/cm³ was selected. The selected toner particles (100 parts) were then mixed with 0.6 part of hydrophobic silica to obtain a toner. This toner was charged in a toner container of an image forming machine (imagio MF2230 manufactured by Ricoh Company, Ltd.), and an image was produced. The image was found to have an image density of 1.40 and color reproducibility of a* = 0.1, b* = -0.5. Thus the image quality was comparable to that obtained by using the conventional carbon black toner. The consumption of the toner and carrier service life were tested by repeatedly producing images for long runs. The results were similar to those obtained by using the conventional carbon black toner.

Example 2

[0039]

Polyester resin	76 parts
Carbauna wax	5 parts
TiFe Ferrite (number average particle diameter: 96 nm, saturation magnetization: 3.0 Am ² /Kg)	23 parts
Metal salt of salicylic acid compound	3 parts

[0040] The above composition was mixed using a Henschel mixer under various conditions to obtain premixed ma-

terials having different degrees of mixing state and each having a weight particle diameter of 9.0 μm . Each of the premixed materials was melted, kneaded with a dual axis kneader, solidified, ground and classified. From the thus obtained various kinds of toner particles having different degree of mixing state, one kind of toner particles having a dielectric loss δ of 3×10^{-3} and a true specific gravity of 1.36 g/cm^3 was selected. The selected toner particles (100 parts) were then mixed with 0.5 part of hydrophobic silica to obtain a toner. This toner was charged in a toner container of an image forming machine (imagio MF2230 manufactured by Ricoh Company, Ltd.), and an image was produced. The image was found to have an image density of 1.33 and color reproducibility of $a^* = -0.0$, $b^* = -0.2$. Thus the image quality was comparable to that obtained by using the conventional carbon black toner. The consumption of the toner and carrier service life were tested by repeatedly producing images for long runs. The results were similar to those obtained by using the conventional carbon black toner.

Example 3

[0041]

Polyester resin	74 parts
Polyethylene wax	5 parts
$\text{Fe}_2\text{O}_3\text{-Mn}_2\text{O}_3$ (number average particle diameter: 55 nm, saturation magnetization: 2.0 Am^2/Kg)	20 parts
Negative charge controlling agent	1 part

[0042] The above composition was mixed using a Henschel mixer under various conditions to obtain premixed materials having different degrees of mixing state and each having a weight particle diameter of 11.5 μm . Each of the premixed materials was melted, kneaded with a dual axis kneader, solidified, ground and classified. From the thus obtained various kinds of toner particles having different degree of mixing state, one kind of toner particles having a dielectric loss δ of 4×10^{-3} and a true specific gravity of 1.41 g/cm^3 was selected. The selected toner particles (100 parts) were then mixed with 0.4 part of hydrophobic silica to obtain a toner. This toner was charged in a toner container of an image forming machine (imagio MF2230 manufactured by Ricoh Company, Ltd.), and an image was produced. The image was found to have an image density of 1.35 and color reproducibility of $a^* = -0.1$, $b^* = -0.3$. Thus the image quality was comparable to that obtained by using the conventional carbon black toner. The consumption of the toner and carrier service life were tested by repeatedly producing images for long runs. The results were similar to those obtained by using the conventional carbon black toner.

Example 4

[0043]

Styrene-acrylate resin	67 parts
Low molecular weight polypropylene	5 parts
Titanium oxide sintered material (number average particle diameter: 30 nm, saturation magnetization: 0.5 Am^2/Kg)	27 parts
Negative charge controlling agent	1 part

[0044] The above composition was mixed using a Henschel mixer under various conditions to obtain premixed materials having different degrees of mixing state and each having a weight particle diameter of 5.5 μm . Each of the premixed materials was melted, kneaded with a dual axis kneader, solidified, ground and classified. From the thus obtained various kinds of toner particles having different degree of mixing state, one kind of toner particles having a dielectric loss δ of 13×10^{-3} and a true specific gravity of 1.51 g/cm^3 was selected. The selected toner particles (100 parts) were then mixed with 0.9 part of hydrophobic silica to obtain a toner. This toner was charged in a toner container of an image forming machine (imagio MF2230 manufactured by Ricoh Company, Ltd.), and an image was produced. The image was found to have an image density of 1.42 and color reproducibility of $a^* = -0.2$, $b^* = -0.3$. Thus the image quality was comparable to that obtained by using the conventional carbon black toner. The consumption of the toner and carrier service life were tested by repeatedly producing images for long runs. The results were similar to those

obtained by using the conventional carbon black toner.

Example 5

[0045]

Polyester resin	54 parts
Carbauna wax	5 parts
TiFe Ferrite (number average particle diameter: 72 nm, saturation magnetization: 0.5 Am ² /Kg)	40 parts
Negative charge controlling agent	1 part

[0046] The above composition was mixed using a Henschel mixer under various conditions to obtain premixed materials having different degrees of mixing state and each having a weight particle diameter of 7.0 μm . Each of the premixed materials was melted, kneaded with a dual axis kneader, solidified, ground and classified. From the thus obtained various kinds of toner particles having different degree of mixing state, one kind of toner particles having a dielectric loss δ of 10×10^{-3} and a true specific gravity of 1.72 g/cm³ was selected. The selected toner particles (100 parts) were then mixed with 0.6 part of hydrophobic silica to obtain a toner. This toner was charged in a toner container of an image forming machine (imagio MF2230 manufactured by Ricoh Company, Ltd.), and an image was produced. The image was found to have an image density of 1.45 and color reproducibility of $a^* = 0.1$, $b^* = 0.0$. Thus the image quality was comparable to that obtained by using the conventional carbon black toner. The consumption of the toner and carrier service life were tested by repeatedly producing images for long runs. The results of the toner consumption were similar to those obtained by using the conventional carbon black toner. However, the carrier life was about 90 % of that of the conventional carbon black toner.

Comparative Example 1

[0047]

Polyester resin	74 parts
Polyethylene wax	5 parts
MnFe Ferrite (number average particle diameter: 15 nm, saturation magnetization: 0.2 Am ² /Kg)	20 parts
Negative charge controlling agent	1 part

[0048] The above composition was mixed using a Henschel mixer under various conditions to obtain premixed materials having different degrees of mixing state and each having a weight particle diameter of 7.0 μm . Each of the premixed materials was melted, kneaded with a dual axis kneader, solidified, ground and classified. From the thus obtained various kinds of toner particles having different degree of mixing state, one kind of toner particles having the lowest dielectric loss δ of 20×10^{-3} and a true specific gravity of 1.41 g/cm³ was selected. The selected toner particles (100 parts) were then mixed with 0.6 part of hydrophobic silica to obtain a toner. This toner was charged in a toner container of an image forming machine (imagio MF2230 manufactured by Ricoh Company, Ltd.), and an image was produced. The image was found to have an image density of 1.45 and color reproducibility of $a^* = -0.1$, $b^* = -0.2$. Thus the image quality was comparable to that obtained by using the conventional carbon black toner. The consumption of the toner was tested by repeatedly producing images for long runs. The consumption was 1.5 times as large as that of the conventional carbon black toner.

Comparative Example 2

[0049]

Polyester resin	74 parts
Polyethylene wax	5 parts

(continued)

MnFe Ferrite (number average particle diameter: 140 nm, saturation magnetization: 0.2 Am ² /Kg)	20 parts
Negative charge controlling agent	1 part

[0050] The above composition was mixed using a Henschel mixer under various conditions to obtain premixed materials having different degrees of mixing state and each having a weight particle diameter of 7.0 μm . Each of the premixed materials was melted, kneaded with a dual axis kneader, solidified, ground and classified. From the thus obtained various kinds of toner particles having different degree of mixing state, one kind of toner particles having a dielectric loss δ of 6×10^{-3} and a true specific gravity of 1.42 g/cm³ was selected. The selected toner particles (100 parts) were then mixed with 0.6 part of hydrophobic silica to obtain a toner. This toner was charged in a toner container of an image forming machine (imagio MF2230 manufactured by Ricoh Company, Ltd.), and an image was produced. The image was found to have an image density of 1.15 and color reproducibility of $a^* = 0.2$, $b^* = 0.1$. Thus the image quality was not good as compared with the conventional carbon black toner.

Comparative Example 3

[0051]

Polyester resin	44 parts
Polyethylene wax	5 parts
TiFe Ferrite (number average particle diameter: 120 nm, saturation magnetization: 0.5 Am ² /Kg)	50 parts
Negative charge controlling agent	1 part

[0052] The above composition was mixed using a Henschel mixer under various conditions to obtain premixed materials having different degrees of mixing state and each having a weight particle diameter of 7.0 μm . Each of the premixed materials was melted, kneaded with a dual axis kneader, solidified, ground and classified. From the thus obtained various kinds of toner particles having different degree of mixing state, one kind of toner particles having a dielectric loss δ of 8×10^{-3} and a true specific gravity of 1.89 g/cm³ was selected. The selected toner particles (100 parts) were then mixed with 0.6 part of hydrophobic silica to obtain a toner. This toner was charged in a toner container of an image forming machine (imagio MF2230 manufactured by Ricoh Company, Ltd.), and an image was produced. The image was found to have an image density of 1.42 and color reproducibility of $a^* = 0.3$, $b^* = -0.6$. Thus the image quality was comparable to that obtained by using the conventional carbon black toner. The consumption of the toner and carrier service life were tested by repeatedly producing images for long runs. The results of the toner consumption were similar to those obtained by using the conventional carbon black toner. However, the carrier life was about 60 % of that of the conventional carbon black toner.

Comparative Example 4

[0053]

Polyester resin	74 parts
Polyethylene wax	5 parts
TiFe Ferrite (number average particle diameter: 72 nm, saturation magnetization: 0.5 Am ² /Kg)	20 parts
Negative charge controlling agent	1 part

[0054] The above composition was mixed using a Henschel mixer under various conditions to obtain premixed materials having different degrees of mixing state and each having a weight particle diameter of 7.0 μm . Each of the premixed materials was melted, kneaded with a dual axis kneader, solidified, ground and classified. From the thus obtained various kinds of toner particles having different degree of mixing state, one kind of toner particles having a

dielectric loss δ of $2 \cdot 10^{-3}$ and a true specific gravity of 1.40 g/cm^3 was selected. The selected toner particles (100 parts) were then mixed with 0.6 part of hydrophobic silica to obtain a toner. This toner was charged in a toner container of an image forming machine (imagio MF2230 manufactured by Ricoh Company, Ltd.), and an image was produced. The image was found to have an image density of 1.15 and color reproducibility of $a^* = -0.4$, $b^* = 0.3$. Thus the image quality was not good as compared with the conventional carbon black toner.

Comparative Example 5

[0055]

Polyester resin	74 parts
Polyethylene wax	5 parts
TiFe Ferrite (number average particle diameter: 72 nm, saturation magnetization: $0.5 \text{ Am}^2/\text{Kg}$)	20 parts
Negative charge controlling agent	1 part

[0056] The above composition was mixed using a Henschel mixer under various conditions to obtain premixed materials having different degrees of mixing state and each having a weight particle diameter of $7.0 \mu\text{m}$. Each of the premixed materials was melted, kneaded with a dual axis kneader, solidified, ground and classified. From the thus obtained various kinds of toner particles having different degree of mixing state, one kind of toner particles having a dielectric loss δ of 30×10^{-3} and a true specific gravity of 1.41 g/cm^3 was selected. The selected toner particles (100 parts) were then mixed with 0.6 part of hydrophobic silica to obtain a toner. This toner was charged in a toner container of an image forming machine (imagio MF2230 manufactured by Ricoh Company, Ltd.), and an image was produced. The image was found to have an image density of 1.45 and color reproducibility of $a^* = -0.5$, $b^* = 0.2$. Thus the image quality was comparable to that obtained by using the conventional carbon black toner. The consumption of the toner was tested by repeatedly producing images for long runs. The toner consumption was about 2 times as large as that of the conventional carbon black toner.

Comparative Example 6

[0057]

Polyester resin	86 parts
Polyethylene wax	5 parts
TiFe Ferrite (number average particle diameter: 100 nm, saturation magnetization: $0.5 \text{ Am}^2/\text{Kg}$)	8 parts
Negative charge controlling agent	1 part

[0058] The above composition was mixed using a Henschel mixer under various conditions to obtain premixed materials having different degrees of mixing state and each having a weight particle diameter of $7.0 \mu\text{m}$. Each of the premixed materials was melted, kneaded with a dual axis kneader, solidified, ground and classified. From the thus obtained various kinds of toner particles having different degree of mixing state, one kind of toner particles having a dielectric loss δ of 2×10^{-3} and a true specific gravity of 1.40 g/cm^3 was selected. The selected toner particles (100 parts) were then mixed with 0.6 part of hydrophobic silica to obtain a toner. This toner was charged in a toner container of an image forming machine (imagio MF2230 manufactured by Ricoh Company, Ltd.), and an image was produced. The image was found to have an image density of 1.05 and color reproducibility of $a^* = -0.2$, $b^* = -0.4$. Thus the image quality was not good as compared with the conventional carbon black toner.

Example 6

[0059]

Polyester resin	64 parts
-----------------	----------

EP 1 343 053 A1

(continued)

Polyethylene wax	5 parts
TiFe Ferrite (number average particle diameter: 72 nm, saturation magnetization: 12 Am ² /Kg)	30 parts
Negative charge controlling agent	1 part

[0060] The above composition was mixed using a Henschel mixer under various conditions to obtain premixed materials having different degrees of mixing state and each having a weight particle diameter of 7.0 μm . Each of the premixed materials was melted, kneaded with a dual axis kneader, solidified, ground and classified. From the thus obtained various kinds of toner particles having different degree of mixing state, one kind of toner particles having a dielectric loss δ of 8×10^{-3} and a true specific gravity of 1.54 g/cm³ was selected. The selected toner particles (100 parts) were then mixed with 0.6 part of hydrophobic silica to obtain a toner. This toner was charged in a toner container of an image forming machine (imagio MF2230 manufactured by Ricoh Company, Ltd.), and an image was produced. The image was found to have an image density of 1.23 and color reproducibility of $a^* = -0.1$, $b^* = -0.5$. Thus the image density was lower as compared with the conventional carbon black toner. The consumption of the toner was tested by repeatedly producing images for long runs. The toner consumption was smaller than that of the conventional carbon black toner.

Example 7

[0061]

Polyester resin	71 parts
Polyethylene wax	5 parts
MnFe Ferrite (number average particle diameter: 72 nm, saturation magnetization: 0.2 Am ² /Kg)	23 parts
Negative charge controlling agent	1 part

[0062] The above composition was mixed using a Henschel mixer under various conditions to obtain premixed materials having different degrees of mixing state and each having a weight particle diameter of 7.0 μm . Each of the premixed materials was melted, kneaded with a dual axis kneader, solidified, ground and classified. From the thus obtained various kinds of toner particles having different degree of mixing state, one kind of toner particles having a dielectric loss δ of 12×10^{-3} and a true specific gravity of 1.44 g/cm³ was selected. The selected toner particles (100 parts) were then mixed with 0.5 part of hydrophobic silica under the following conditions to obtain a toner.

Henschel mixer: Type 20B

Revolution speed of the mixer: 1890 rpm

Operation pattern: operated for 30 seconds and then stopped for 60 seconds

Mixing time: the above operation was repeated 12 times.

[0063] The thus obtained toner was found to have a detaching rate of 0.05 %. The toner was charged in a toner container of an image forming machine (imagio MF2230 manufactured by Ricoh Company, Ltd.), and an image was produced. The image was found to have an image density of 1.35 and color reproducibility of $a^* = -0.1$, $b^* = -0.5$. Thus the image quality was comparable to that obtained by using the conventional carbon black toner. The image production was repeated for 60, 000 runs. The 60, 000th image had an image density of 1.34 and good color reproducibility. The toner consumption and carrier life were good. Also measured were toner scattering and background stains. The results are summarized in Table 1.

Example 8

[0064]

Polyester resin	71 parts
Polyethylene wax	5 parts
MnFe Ferrite (number average particle diameter: 72 nm, saturation magnetization: 0.2 Am ² /Kg)	23 parts
Negative charge controlling agent	1 part

(continued)

diameter: 72 nm, saturation magnetization: 0.2 Am ² /Kg	23 parts
Negative charge controlling agent	1 part

[0065] The above composition was mixed using a Henschel mixer under various conditions to obtain premixed materials having different degrees of mixing state and each having a weight particle diameter of 7.0 μm . Each of the premixed materials was melted, kneaded with a dual axis kneader, solidified, ground and classified. From the thus obtained various kinds of toner particles having different degree of mixing state, one kind of toner particles having a dielectric loss δ of 12×10^{-3} and a true specific gravity of 1.44 g/cm³ was selected. The selected toner particles (100 parts) were then mixed with 0.8 part of hydrophobic silica under the following conditions to obtain a toner.

Henschel mixer: Type 20B

Revolution speed of the mixer: 1890 rpm

Operation pattern: operated for 30 seconds and then stopped for 60 seconds

Mixing time: the above operation was repeated 12 times.

[0066] The thus obtained toner was found to have a detaching rate of 0.08 %. The toner was charged in a toner container of an image forming machine (imagio MF2230 manufactured by Ricoh Company, Ltd.), and an image was produced. The image was found to have an image density of 1.33 and color reproducibility of $a^* = -0.1$, $b^* = -0.5$. Thus the image quality was comparable to that obtained by using the conventional carbon black toner. The image production was repeated for 60,000 runs. The 60,000th image had an image density of 1.34 and good color reproducibility. The toner consumption and carrier life were good. Also measured were toner scattering and background stains. The results are summarized in Table 1.

Example 9

[0067]

Polyester resin	76 parts
Carnauba wax	5 parts
TiFe Ferrite (number average particle diameter: 96 nm, saturation magnetization: 3.0 Am ² /Kg)	23 parts
Metal salt of salicylic acid compound	3 parts

[0068] The above composition was mixed using a Henschel mixer under various conditions to obtain premixed materials having different degrees of mixing state and each having a weight particle diameter of 9.0 μm . Each of the premixed materials was melted, kneaded with a dual axis kneader, solidified, ground and classified. From the thus obtained various kinds of toner particles having different degree of mixing state, one kind of toner particles having a dielectric loss δ of 3×10^{-3} and a true specific gravity of 1.36 g/cm³ was selected. The selected toner particles (100 parts) were then mixed with 0.6 part of hydrophobic silica under the following conditions to obtain a toner.

Henschel mixer: Type 20B

Revolution speed of the mixer: 1890 rpm

Operation pattern: operated for 30 seconds and then stopped for 60 seconds

Mixing time: the above operation was repeated 12 times.

[0069] The thus obtained toner was found to have a detaching rate of 0.05 %. The toner was charged in a toner container of an image forming machine (imagio MF2230 manufactured by Ricoh Company, Ltd.), and an image was produced. The image was found to have an image density of 1.33 and color reproducibility of $a^* = -0.0$, $b^* = -0.2$. Thus the image quality was comparable to that obtained by using the conventional carbon black toner. The image production was repeated for 60,000 runs. The 60,000th image had an image density of 1.33 and good color reproducibility. The toner consumption and carrier life were good. Also measured were toner scattering and background stains. The results are summarized in Table 1.

Example 10

[0070]

Polyester resin	74 parts
Polyethylene wax	5 parts
Fe ₂ O ₃ -Mn ₂ O ₃ (number average particle diameter: 55 nm, saturation magnetization: 2.0 Am ² /Kg)	20 parts
Negative charge controlling agent	1 part

[0071] The above composition was mixed using a Henschel mixer under various conditions to obtain premixed materials having different degrees of mixing state and each having a weight particle diameter of 11.5 μm . Each of the premixed materials was melted, kneaded with a dual axis kneader, solidified, ground and classified. From the thus obtained various kinds of toner particles having different degree of mixing state, one kind of toner particles having a dielectric loss δ of 4×10^{-3} and a true specific gravity of 1.41 g/cm³ was selected. The selected toner particles (100 parts) were then mixed with 0.5 part of hydrophobic silica under the following conditions to obtain a toner.

Henschel mixer: Type 20B

Revolution speed of the mixer: 1890 rpm

Operation pattern: operated for 30 seconds and then stopped for 60 seconds

Mixing time: the above operation was repeated 12 times.

[0072] The thus obtained toner was found to have a detaching rate of 0.05 %. The toner was charged in a toner container of an image forming machine (imagio MF2230 manufactured by Ricoh Company, Ltd.), and an image was produced. The image was found to have an image density of 1.38 and color reproducibility of $a^* = -0.1$, $b^* = -0.3$. Thus the image quality was comparable to that obtained by using the conventional carbon black toner. The image production was repeated for 60,000 runs. The 60,000th image had an image density of 1.35 and good color reproducibility. The toner consumption and carrier life were good. Also measured were toner scattering and background stains. The results are summarized in Table 1.

Example 11

[0073]

Styrene-acrylate resin	67 parts
Low molecular weight polypropylene	5 parts
Titanium oxide sintered material (number average particle diameter: 30 nm, saturation magnetization: 0.5 Am ² /Kg)	27 parts
Negative charge controlling agent	1 part

[0074] The above composition was mixed using a Henschel mixer under various conditions to obtain premixed materials having different degrees of mixing state and each having a weight particle diameter of 5.5 μm . Each of the premixed materials was melted, kneaded with a dual axis kneader, solidified, ground and classified. From the thus obtained various kinds of toner particles having different degree of mixing state, one kind of toner particles having a dielectric loss δ of 13×10^{-3} and a true specific gravity of 1.51 g/cm³ was selected. The selected toner particles (100 parts) were then mixed with 0.5 part of hydrophobic silica under the following conditions to obtain a toner.

Henschel mixer: Type 20B

Revolution speed of the mixer: 1890 rpm

Operation pattern: operated for 30 seconds and then stopped for 60 seconds

Mixing time: the above operation was repeated 12 times.

[0075] The thus obtained toner was found to have a detaching rate of 0.05 %. The toner was charged in a toner container of an image forming machine (imagio MF2230 manufactured by Ricoh Company, Ltd.), and an image was produced. The image was found to have an image density of 1.42 and color reproducibility of $a^* = -0.2$, $b^* = -0.3$. Thus the image quality was comparable to that obtained by using the conventional carbon black toner. The image production was repeated for 60,000 runs. The 60,000th image had an image density of 1.40 and good color reproducibility. The

toner consumption and carrier life were good. Also measured were toner scattering and background stains. The results are summarized in Table 1.

Example 12

[0076]

Polyester resin	54 parts
Carbauna wax	5 parts
TiFe Ferrite (number average particle diameter: 96 nm, saturation magnetization: 3.0 Am ² /Kg)	16 parts
Metal salt of salicylic acid compound	3 parts

[0077] The above composition was mixed using a Henschel mixer under various conditions to obtain premixed materials having different degrees of mixing state and each having a weight particle diameter of 9.0 μm . Each of the premixed materials was melted, kneaded with a dual axis kneader, solidified, ground and classified. From the thus obtained various kinds of toner particles having different degree of mixing state, one kind of toner particles having a dielectric loss δ of 3×10^{-3} and a true specific gravity of 1.36 g/cm³ was selected. The selected toner particles (100 parts) were then mixed with 0.5 part of hydrophobic silica under the following conditions to obtain a toner.

Henschel mixer: Type 20B

Revolution speed of the mixer: 1890 rpm

Operation pattern: operated for 30 seconds and then stopped for 60 seconds

Mixing time: the above operation was repeated 12 times.

[0078] The thus obtained toner was found to have a detaching rate of 0.05 %. The toner was charged in a toner container of an image forming machine (imagio MF2230 manufactured by Ricoh Company, Ltd.), and an image was produced. The image was found to have an image density of 1.35 and color reproducibility of $a^* = -0.0$, $b^* = -0.2$. Thus the image quality was comparable to that obtained by using the conventional carbon black toner. The image production was repeated for 60,000 runs. The 60,000th image had an image density of 1.33 and good color reproducibility. The toner consumption and carrier life were good. Also measured were toner scattering and background stains. The results are summarized in Table 1.

Example 13

[0079]

Polyester resin	71 parts
Polyethylene wax	5 parts
MnFe Ferrite (number average particle diameter: 72 nm, saturation magnetization: 0.2 Am ² /Kg)	23 parts
Negative charge controlling agent	1 part

[0080] The above composition was mixed using a Henschel mixer under various conditions to obtain premixed materials having different degrees of mixing state and each having a weight particle diameter of 7.0 μm . Each of the premixed materials was melted, kneaded with a dual axis kneader, solidified, ground and classified. From the thus obtained various kinds of toner particles having different degree of mixing state, one kind of toner particles having a dielectric loss δ of 12×10^{-3} and a true specific gravity of 1.44 g/cm³ was selected. The selected toner particles (100 parts) were then mixed with 0.5 part of hydrophobic silica under the following conditions to obtain a toner.

Henschel mixer: Type 20B

Revolution speed of the mixer: 1890 rpm

Operation pattern: operated for 30 seconds and then stopped for 60 seconds

Mixing time: the above operation was repeated 8 times.

[0081] The thus obtained toner was found to have a detaching rate of 0.14 %. The toner was charged in a toner container of an image forming machine (imagio MF2230 manufactured by Ricoh Company, Ltd.), and an image was produced. The image was found to have an image density of 1.35 and color reproducibility of $a^* = -0.1$, $b^* = -0.5$. Thus

EP 1 343 053 A1

the image quality was comparable to that obtained by using the conventional carbon black toner. The image production was repeated for 60,000 runs. The 60, 000th image had an image density of 1.34 and good color reproducibility. The toner consumption and carrier life were good. Also measured were toner scattering and background stains. The results are summarized in Table 1.

Comparative Example 7

[0082]

Polyester resin	74 parts
Polyethylene wax	5 parts
TiFe Ferrite (number average particle diameter: 72 nm, saturation magnetization: 0.5 Am ² /Kg)	20 parts
Negative charge controlling agent	1 part

[0083] The above composition was mixed using a Henschel mixer under various conditions to obtain premixed materials having different degrees of mixing state and each having a weight particle diameter of 7.0 μm . Each of the premixed materials was melted, kneaded with a dual axis kneader, solidified, ground and classified. From the thus obtained various kinds of toner particles having different degree of mixing state, one kind of toner particles having a dielectric loss δ of 2×10^{-3} and a true specific gravity of 1.40 g/cm³ was selected. The selected toner particles (100 parts) were then mixed with 0.6 part of hydrophobic silica under the following conditions to obtain a toner.

Henschel mixer: Type 20B

Revolution speed of the mixer: 1890 rpm

Operation pattern: operated for 30 seconds and then stopped for 60 seconds

Mixing time: the above operation was conducted only once.

[0084] The thus obtained toner was found to have a detaching rate of 0.20 %. The toner was charged in a toner container of an image forming machine (imagio MF2230 manufactured by Ricoh Company, Ltd.), and an image was produced. The image was found to have an image density of 1.15 and color reproducibility of $a^* = -0.4$, $b^* = 0.3$. The image production was repeated for 60, 000 runs. Good image quality was not obtainable after long runs. The results are summarized in Table 1.

Comparative Example 8

[0085]

Polyester resin	74 parts
Polyethylene wax	5 parts
TiFe Ferrite (number average particle diameter: 72 nm, saturation magnetization: 0.5 Am ² /Kg)	20 parts
Negative charge controlling agent	1 part

[0086] The above composition was mixed using a Henschel mixer under various conditions to obtain premixed materials having different degrees of mixing state and each having a weight particle diameter of 7.0 μm . Each of the premixed materials was melted, kneaded with a dual axis kneader, solidified, ground and classified. From the thus obtained various kinds of toner particles having different degree of mixing state, one kind of toner particles having a dielectric loss δ of 30×10^{-3} and a true specific gravity of 1.41 g/cm³ was selected. The selected toner particles (100 parts) were then mixed with 0.6 part of hydrophobic silica under the following conditions to obtain a toner.

Henschel mixer: Type 20B

Revolution speed of the mixer: 1890 rpm

Operation pattern: operated for 30 seconds and then stopped for 60 seconds

Mixing time: the above operation was conducted only once.

[0087] The thus obtained toner was found to have a detaching rate of 0.20 %. The toner was charged in a toner container of an image forming machine (imagio MF2230 manufactured by Ricoh Company, Ltd.), and an image was produced. The image was found to have an image density of 1.45 and color reproducibility of $a^* = -0.5$, $b^* = 0.2$. Thus

the image quality was comparable to that obtained by using the conventional carbon black toner. The image production was repeated for 60,000 runs. Good image quality was not obtainable after long runs. The results are summarized in Table 1.

Comparative Example 9

[0088]

Polyester resin	64 parts
Polyethylene wax	5 parts
TiFe Ferrite (number average particle diameter: 72 nm, saturation magnetization: 12 Am ² /Kg)	30 parts
Negative charge controlling agent	1 part

[0089] The above composition was mixed using a Henschel mixer under various conditions to obtain premixed materials having different degrees of mixing state and each having a weight particle diameter of 7.0 μm . Each of the premixed materials was melted, kneaded with a dual axis kneader, solidified, ground and classified. From the thus obtained various kinds of toner particles having different degree of mixing state, one kind of toner particles having a dielectric loss δ of 8×10^{-3} and a true specific gravity of 1.54 g/cm³ was selected. The selected toner particles (100 parts) were then mixed with 0.6 part of hydrophobic silica under the following conditions to obtain a toner.

Henschel mixer: Type 20B

Revolution speed of the mixer: 1890 rpm

Operation pattern: operated for 30 seconds and then stopped for 60 seconds

Mixing time: the above operation was conducted only once.

[0090] The thus obtained toner was found to have a detaching rate of 0.20 %. The toner was charged in a toner container of an image forming machine (imaggio MF2230 manufactured by Ricoh Company, Ltd.), and an image was produced. The image was found to have an image density of 1.23 and color reproducibility of $a^* = -0.1$, $b^* = -0.5$. Thus the image quality was comparable to that obtained by using the conventional carbon black toner. The image production was repeated for 60,000 runs. Good image quality was not obtainable after long runs. The results are summarized in Table 1.

Table 1

Example No.	Amount of Silica (part)	Detaching rate (wt. %)	Initial		After 60000 image production			
			Image quality	Image density	Image quality	Image density	Toner scattering	Back-ground stains
7	0.5	10.0	good	1.35	good	1.34	none	none
8	0.8	10.0	good	1.33	good	1.32	none	none
9	0.6	8.3	good	1.33	good	1.33	none	none
10	0.5	10.0	good	1.38	good	1.35	none	none
11	0.5	10.0	good	1.42	good	1.40	none	none
12	0.5	10.0	good	1.35	good	1.33	none	none
13	0.5	28.0	good	1.35	good	1.34	none	none
Comp. 7	0.6	33.3	good	1.15	no good	1.11	none	occurred
Comp. 8	0.6	33.3	good	1.45	no good	1.42	occurred	occurred
Comp. 9	0.6	33.3	good	1.23	no good	1.20	occurred	none

Example 14

[0091]

Polyester resin	71 parts
Polyethylene wax	5 parts
MnFe Ferrite (number average particle diameter: 72 nm, saturation magnetization: 0.2 Am ² /Kg)	23 parts
Negative charge controlling agent	1 part

[0092] The above composition was mixed using a Henschel mixer under various conditions to obtain premixed materials having different degrees of mixing state and each having a weight particle diameter of 7.0 μm . Each of the premixed materials was melted, kneaded with a dual axis kneader, solidified, ground and classified. From the thus obtained various kinds of toner particles having different degree of mixing state, one kind of toner particles having a dielectric loss δ of 12×10^{-3} and a true specific gravity of 1.44 g/cm³ was selected. The selected toner particles (100 parts) were then mixed with 0.5 part of hydrophobic silica under the following conditions to obtain a toner.

Henschel mixer: Type 20B

Revolution speed of the mixer: 1890 rpm

Operation pattern: operated for 30 seconds and then stopped for 60 seconds

Mixing time: the above operation was repeated 12 times, namely, a total mixing time (T) was 360 seconds

Clearance C between the tip of the blade and the inside wall: 0.01 m

[0093] Peripheral speed V of the tip of the blade: 49.5 m/sec The $(C \times d)/(V \times T)$ value (d represents the number average particle diameter of the black metal oxide) was thus 4.0×10^{-14} m. The toner was charged in a toner container of an image forming machine (imagio MF2230 manufactured by Ricoh Company, Ltd.), and an image was produced. The image was found to have an image density of 1.35 and color reproducibility of $a^* = -0.1$, $b^* = -0.5$. Thus the image quality was comparable to that obtained by using the conventional carbon black toner. The image production was repeated for 60,000 runs. The 20,000th and 60,000th images were found to have good image quality (preciseness).

Example 15

[0094]

Polyester resin	71 parts
Polyethylene wax	5 parts
MnFe Ferrite (number average particle diameter: 72 nm, saturation magnetization: 0.2 Am ² /Kg)	23 parts
Negative charge controlling agent	1 part

[0095] The above composition was mixed using a Henschel mixer under various conditions to obtain premixed materials having different degrees of mixing state and each having a weight particle diameter of 7.0 μm . Each of the premixed materials was melted, kneaded with a dual axis kneader, solidified, ground and classified. From the thus obtained various kinds of toner particles having different degree of mixing state, one kind of toner particles having a dielectric loss δ of 12×10^{-3} and a true specific gravity of 1.44 g/cm³ was selected. The selected toner particles (100 parts) were then mixed with 0.8 part of hydrophobic silica under the following conditions to obtain a toner.

Henschel mixer: Type 20B

Revolution speed of the mixer: 1890 rpm

Operation pattern: operated for 30 seconds and then stopped for 60 seconds

Mixing time: the above operation was repeated 12 times, namely, a total mixing time (T) was 360 seconds

Clearance C between the tip of the blade and the inside wall: 0.005 m

Peripheral speed V of the tip of the blade: 49.5 m/sec

The $(C \times d)/(V \times T)$ value (d represents the number average particle diameter of the black metal oxide) was thus 2.0×10^{-14} m. The toner was charged in a toner container of an image forming machine (imagio MF2230 manufactured by Ricoh Company, Ltd.), and an image was produced. The image was found to have an image density of 1.33 and color reproducibility of $a^* = -0.1$, $b^* = -0.5$. Thus the image quality was comparable to that obtained by using the con-

EP 1 343 053 A1

ventional carbon black toner. The image production was repeated for 60,000 runs. The 20,000th and 60,000th images were found to have good image quality (preciseness).

Example 16

[0096]

Polyester resin	76 parts
Carnauba wax	5 parts
TiFe Ferrite (number average particle diameter: 96 nm, saturation magnetization: 3.0 Am ² /Kg)	23 parts
Metal salt of salicylic acid compound	3 parts

[0097] The above composition was mixed using a Henschel mixer under various conditions to obtain premixed materials having different degrees of mixing state and each having a weight particle diameter of 9.0 μm. Each of the premixed materials was melted, kneaded with a dual axis kneader, solidified, ground and classified. From the thus obtained various kinds of toner particles having different degree of mixing state, one kind of toner particles having a dielectric loss δ of 5×10^{-3} and a true specific gravity of 1.36 g/cm³ was selected. The selected toner particles (100 parts) were then mixed with 0.6 part of hydrophobic silica under the following conditions to obtain a toner.

Henschel mixer: Type 20B

Revolution speed of the mixer: 1890 rpm

Operation pattern: operated for 30 seconds and then stopped for 60 seconds

Mixing time: the above operation was repeated 36 times,

namely, a total mixing time (T) was 1080 seconds Clearance C between the tip of the blade and the inside wall: 0.01 m

[0098] Peripheral speed V of the tip of the blade: 49.5 m/sec The $(C \times d)/(V \times T)$ value (d represents the number average particle diameter of the black metal oxide) was thus 1.8×10^{-14} m. The toner was charged in a toner container of an image forming machine (imagio MF2230 manufactured by Ricoh Company, Ltd.), and an image was produced. The image was found to have an image density of 1.33 and color reproducibility of $a^* = -0.1$, $b^* = -0.2$. Thus the image quality was comparable to that obtained by using the conventional carbon black toner. The image production was repeated for 60,000 runs. The 20,000th and 60,000th images were found to have good image quality (preciseness).

Example 17

[0099]

Polyester resin	74 parts
Polyethylene wax	5 parts
Fe ₂ O ₃ -Mn ₂ O ₃ (number average particle diameter: 55 nm, saturation magnetization: 2.0 Am ² /Kg)	20 parts
Negative charge controlling agent	1 part

[0100] The above composition was mixed using a Henschel mixer under various conditions to obtain premixed materials having different degrees of mixing state and each having a weight particle diameter of 11.5 μm. Each of the premixed materials was melted, kneaded with a dual axis kneader, solidified, ground and classified. From the thus obtained various kinds of toner particles having different degree of mixing state, one kind of toner particles having a dielectric loss δ of 4×10^{-3} and a true specific gravity of 1.41 g/cm³ was selected. The selected toner particles (100 parts) were then mixed with 0.5 part of hydrophobic silica under the following conditions to obtain a toner.

Henschel mixer: Type 20B

Revolution speed of the mixer: 1890 rpm

Operation pattern: operated for 30 seconds and then stopped for 60 seconds

Mixing time: the above operation was repeated 12 times,

namely, a total mixing time (T) was 360 seconds Clearance C between the tip of the blade and the inside wall: 0.01 m

[0101] Peripheral speed V of the tip of the blade: 49.5 m/sec The $(C \times d)/(V \times T)$ value (d represents the number average particle diameter of the black metal oxide) was thus 3.1×10^{-14} m. The toner was charged in a toner container of an image forming machine (imagio MF2230 manufactured by Ricoh Company, Ltd.), and an image was produced. The image was found to have an image density of 1.38 and color reproducibility of $a^* = -0.1$, $b^* = -0.3$. Thus the image quality was comparable to that obtained by using the conventional carbon black toner. The image production was repeated for 60,000 runs. The 20,000th and 60,000th images were found to have good image quality (preciseness).

Example 18

[0102]

Styrene-acrylate resin	67 parts
Low molecular weight polypropylene	5 parts
Titanium oxide sintered material (number average particle diameter: 30 nm, saturation magnetization: 0.5 Am ² /Kg)	27 parts
Negative charge controlling agent	1 part

[0103] The above composition was mixed using a Henschel mixer under various conditions to obtain premixed materials having different degrees of mixing state and each having a weight particle diameter of 5.5 μ m. Each of the premixed materials was melted, kneaded with a dual axis kneader, solidified, ground and classified. From the thus obtained various kinds of toner particles having different degree of mixing state, one kind of toner particles having a dielectric loss δ of 13×10^{-3} and a true specific gravity of 1.51 g/cm³ was selected. The selected toner particles (100 parts) were then mixed with 0.5 part of hydrophobic silica under the following conditions to obtain a toner.

Henschel mixer: Type 20B

Revolution speed of the mixer: 1890 rpm

Operation pattern: operated for 30 seconds and then stopped for 60 seconds

Mixing time: the above operation was repeated 24 times,

namely, a total mixing time (T) was 720 seconds Clearance C between the tip of the blade and the inside wall:

0.01 m

[0104] Peripheral speed V of the tip of the blade: 49.5 m/sec The $(C \times d)/(V \times T)$ value (d represents the number average particle diameter of the black metal oxide) was thus 8.4×10^{-14} m. The toner was charged in a toner container of an image forming machine (imagio MF2230 manufactured by Ricoh Company, Ltd.), and an image was produced. The image was found to have an image density of 1.42 and color reproducibility of $a^* = -0.2$, $b^* = -0.3$. Thus the image quality was comparable to that obtained by using the conventional carbon black toner. The image production was repeated for 60,000 runs. The 20,000th and 60,000th images were found to have good image quality (preciseness).

Example 19

[0105]

Polyester resin	54 parts
Carbauna wax	5 parts
TiFe Ferrite (number average particle diameter: 96 nm, saturation magnetization: 3.0 Am ² /Kg)	16 parts
Metal salt of salicylic acid compound	3 parts

[0106] The above composition was mixed using a Henschel mixer under various conditions to obtain premixed materials having different degrees of mixing state and each having a weight particle diameter of 9.0 μ m. Each of the premixed materials was melted, kneaded with a dual axis kneader, solidified, ground and classified. From the thus obtained various kinds of toner particles having different degree of mixing state, one kind of toner particles having a dielectric loss δ of 3×10^{-3} and a true specific gravity of 1.36 g/cm³ was selected. The selected toner particles (100 parts) were then mixed with 0.5 part of hydrophobic silica under the following conditions to obtain a toner.

Henschel mixer: Type 20B

EP 1 343 053 A1

Revolution speed of the mixer: 1890 rpm

Operation pattern: operated for 30 seconds and then stopped for 60 seconds

Mixing time: the above operation was repeated 4 times, namely, a total mixing time (T) was 720 seconds

Clearance C between the tip of the blade and the inside wall: 0.01 m

[0107] Peripheral speed V of the tip of the blade: 49.5 m/sec The $(C \times d)/(V \times T)$ value (d represents the number average particle diameter of the black metal oxide) was thus 2.7×10^{-14} m. The toner was charged in a toner container of an image forming machine, (imagio MF2230 manufactured by Ricoh Company, Ltd.), and an image was produced. The image was found to have an image density of 1.35 and color reproducibility of $a^* = -0.0$, $b^* = -0.2$. Thus the image quality was comparable to that obtained by using the conventional carbon black toner. The image production was repeated for 60,000 runs. The 20,000th and 60,000th images were found to have good image quality (preciseness).

Example 20

[0108]

Polyester resin	71 parts
Polyethylene wax	5 parts
MnFe Ferrite (number average particle diameter: 72 nm, saturation magnetization: 0.2 Am ² /Kg)	23 parts
Negative charge controlling agent	1 part

[0109] The above composition was mixed using a Henschel mixer under various conditions to obtain premixed materials having different degrees of mixing state and each having a weight particle diameter of 7.0 μm. Each of the premixed materials was melted, kneaded with a dual axis kneader, solidified, ground and classified. From the thus obtained various kinds of toner particles having different degree of mixing state, one kind of toner particles having a dielectric loss δ of 12×10^{-3} and a true specific gravity of 1.44 g/cm³ was selected. The selected toner particles (100 parts) were then mixed with 0.5 part of hydrophobic silica under the following conditions to obtain a toner.

Henschel mixer: Type 20B

Revolution speed of the mixer: 1890 rpm

Operation pattern: operated for 30 seconds and then stopped for 60 seconds

Mixing time: the above operation was repeated 12 times, namely, a total mixing time (T) was 360 seconds

Clearance C between the tip of the blade and the inside wall: 0.01 m

[0110] Peripheral speed V of the tip of the blade: 49.5 m/sec The $(C \times d)/(V \times T)$ value (d represents the number average particle diameter of the black metal oxide) was thus 4.0×10^{-14} m. The toner was charged in a toner container of an image forming machine (imagio MF2230 manufactured by Ricoh Company, Ltd.), and an image was produced. The image was found to have an image density of 1.35 and color reproducibility of $a^* = -0.1$, $b^* = -0.5$. Thus the image quality was comparable to that obtained by using the conventional carbon black toner. The image production was repeated for 60,000 runs. The 20,000th and 60,000th images were found to have good image quality (preciseness).

Example 21

[0111]

Polyester resin	74 parts
Polyethylene wax	5 parts
Fe ₂ O ₃ -Mn ₂ O ₃ (number average particle diameter: 55 nm, saturation magnetization: 2.0 Am ² /Kg)	20 parts
Negative charge controlling agent	1 part

[0112] The above composition was mixed using a Henschel mixer under various conditions to obtain premixed materials having different degrees of mixing state and each having a weight particle diameter of 12.5 μm. Each of the premixed materials was melted, kneaded with a dual axis kneader, solidified, ground and classified. From the thus obtained various kinds of toner particles having different degree of mixing state, one kind of toner particles having a dielectric loss δ of 4×10^{-3} and a true specific gravity of 1.41 g/cm³ was selected. The selected toner particles were

used as a toner. The toner was charged in a toner container of an image forming machine (imaggio MF2230 manufactured by Ricoh Company, Ltd.), and an image was produced. The image was found to have an image density of 1.30 and color reproducibility of $a^* = -0.1$, $b^* = -0.3$. Thus the image quality was comparable to that obtained by using the conventional carbon black toner. The consumption of the toner and carrier service life were tested by repeatedly producing images for long runs. The results were similar to those obtained by using the conventional carbon black toner.

[0113] As will be understood from the above results, the black toner according to the present invention can give high quality images with image density comparable to that of the conventional carbon black toner. The black toner is also safe and heat resistant and has good developing efficiency and workability.

Claims

1. A toner for developing an electrostatic latent image, comprising toner particles each including a black colorant and a binder resin, wherein said black colorant comprises a metal oxide having a number average particle diameter in the range of 20 to 100 nm in an amount of 10 to 40 % by weight based on a total weight of said toner particles.
2. A toner as claimed in claim 1, and having a dielectric loss in the range of 3×10^{-3} to 15×10^{-3} .
3. A toner as claimed in claim 1 or 2, wherein the amount of said metal oxide is in the range of 10 to 30 % by weight.
4. A toner as claimed in any preceding claim, and having saturation magnetization of not greater than $10 \text{ Am}^2/\text{Kg}$.
5. A toner as claimed in any preceding claim, further comprising an external additive of fine metal oxide powder in an amount of 0.2 to 5.0 % by weight based on the weight of said toner particles, said fine metal oxide powder being attached to said toner particles such that, when the toner is sonicated in an aqueous medium containing 1 % by weight of a surfactant at a frequency of 38 kHz and a power of 120 W for 10 minutes, the fine metal oxide powder is detached from said toner particles in an amount of 30 % by weight or less based on the weight of said fine metal powder before the toner is sonicated.
6. A toner as claimed in any preceding claim, further comprising an external additive of fine metal oxide powder attached to said toner particles by being mixed with said toner particles using a Henschel mixer for a period of time of T [second],
 said mixer comprising an inside wall defining a mixing chamber, and a rotating blade having a tip portion and disposed in said mixing chamber such that a clearance C [m] is defined between said tip portion and said inside wall, said mixer being operated such that said tip portion of said rotating blade moves at a peripheral speed of V [m/sec],
 wherein said clearance C, peripheral speed V and mixing time T satisfy the following condition:

$$(C \times d) / (V \times T) \leq 5 \times 10^{-13} \text{ [m]}$$
 where d is the number average particle diameter of said metal oxide in unit meter.
7. A toner container containing a toner according to any one of claims 1-6.
8. An image forming apparatus comprising a toner container according to claim 7.
9. An image forming method comprising developing an electrostatic latent image with a toner according to any one of claims 1-6.
10. A method of preparing a toner, comprising mixing toner particles, each including black metal oxide colorant having a number average particle diameter d of 0.02×10^{-6} to 0.100×10^{-6} [m] and a binder resin, with fine metal oxide powder using a Henschel mixer for a period of time of T [second],
 said mixer comprising an inside wall defining a mixing chamber, and a rotating blade having a tip portion and disposed in said mixing chamber such that a clearance C [m] is defined between said tip portion and said inside wall, said mixer being operated such that said tip portion of said rotating blade moves at a peripheral speed of V [m/sec],
 wherein said number average particle diameter d, clearance C, peripheral speed V and mixing time T satisfy

the following condition:

$$(C \times d)/(V \times T) \leq 5 \times 10^{-13}.$$

5

10

15

20

25

30

35

40


45

50

55

BEST AVAILABLE COPY

FIG. 1





European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 03 00 4507

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X A	US 4 282 302 A (MAKINO MOTOHIKO ET AL) 4 August 1981 (1981-08-04) * column 7, line 20 * * column 12, line 19 - line 21 * * column 7 - column 8; example 1 *	1, 3, 7-9 10	G03G9/09 G03G9/097 G03G9/08 G03G9/083
X A	US 5 333 059 A (HYOSU YOSHIHIKO ET AL) 26 July 1994 (1994-07-26) * column 18, line 46 - column 19, line 34; examples 1, 2 * * figure 2 *	1, 4, 5, 7-9 10	
X	US 5 688 852 A (AOKI KOSO ET AL) 18 November 1997 (1997-11-18) * column 28; example 44 * * column 33 - column 34; example 13 *	1, 4, 6-9	
X	EP 0 952 494 A (TODA KOGYO CORP) 27 October 1999 (1999-10-27) * page 16 - page 17; example II * * page 2, line 8 - line 36 *	1, 3, 4, 7-9	
P, X A	EP 1 205 811 A (FUJI XEROX CO LTD) 15 May 2002 (2002-05-15) * page 11; examples A, 1, *	1, 3, 4, 7-9 10	TECHNICAL FIELDS SEARCHED (Int.Cl.7) G03G
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 6 June 2003	Examiner Vogt, C
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03.82 (P4C01)

ANNEX TO THE EUROPEAN SEARCH REPORT ON EUROPEAN PATENT APPLICATION NO.

EP 03 00 4507

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EPP file on. The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

06-06-2003

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 4282302	A	04-08-1981	JP 1404209 C	09-10-1987
			JP 55065406 A	16-05-1980
			JP 60036082 B	19-08-1985
			CA 1129236 A1	10-08-1982
			DE 2966926 D1	24-05-1984
			DK 454879 A ,B,	28-04-1980
			EP 0010732 A1	14-05-1980
US 5333059	A	26-07-1994	JP 3101745 A	26-04-1991
			JP 8016803 B	21-02-1996
			JP 3101746 A	26-04-1991
			JP 8010353 B	31-01-1996
			DE 69020270 D1	27-07-1995
			DE 69020270 T2	16-11-1995
			DE 69033920 D1	04-04-2002
			DE 69033920 T2	18-07-2002
			EP 0417812 A2	20-03-1991
			EP 0646846 A2	05-04-1995
			SG 67317 A1	21-09-1999
US 5688852	A	18-11-1997	US 5126224 A	30-06-1992
			JP 3055333 B2	26-06-2000
			JP 6116504 A	26-04-1994
			JP 6130718 A	13-05-1994
			JP 6130720 A	13-05-1994
			JP 6130719 A	13-05-1994
			CA 2107524 A1	07-04-1994
			DE 69325964 D1	16-09-1999
			DE 69325964 T2	02-12-1999
			EP 0592188 A2	13-04-1994
			US 5470660 A	28-11-1995
			US 5512405 A	30-04-1996
EP 0952494	A	27-10-1999	EP 0952494 A2	27-10-1999
			JP 2000010344 A	14-01-2000
			US 6130017 A	10-10-2000
EP 1205811	A	15-05-2002	JP 2002139865 A	17-05-2002
			JP 2002196528 A	12-07-2002
			CN 1355450 A	26-06-2002
			EP 1205811 A2	15-05-2002
			US 2002076635 A1	20-06-2002

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

THIS PAGE BLANK (USPTO)